



C-400S



CHEMICAL PROPERTIES

SiO ₂	55-60%
Al ₂ O ₃	33-40%
CaO	0.1-0.4%
Fe ₂ O ₃	1-2%
TiO ₂	0.8-1.3%
K ₂ O	1-3.3%
N ₂	30%
MgO	0.1- 2.4%
Na ₂ O	0.2 - 0.6%
Co ₂	70%
N	30%



PHYSICAL PROPERTIES

Specific Gravity(Kg/m ³)	700 - 850
Bulk Density(Kg/m ³)	400 - 450
Particle Size Distribution	2- 425 micron
Compressive Strength (Kg/cm ²)	180 - 280
Sinkers	3-5 % MAX
Color	Light Grey – Light Buff
Melting Point	1200 - 1300°C
pH in water	6 - 8
Moisture	1 % MAX (+/- 1%)
Thermal Conductivity	0.11 w/mk
Hardness (MOH)	5 - 6
Packing Factor	60 - 65%
Shape	Spherical
Wall Thickness	5 - 10% of shell diameter
Loss on ignition	2 % MAX
Oil Absorbtion	16 - 18 G/100G



SIEVE ANALYSIS (MICRON)

+30 # 425 µm	+52 # 300 µm	+100 # 150 µm	+150 # 106 µm	+240 # 63 µm	-240 # 63 µm
0 - 2%	0 - 20 %	15 - 60 %	40 - 90 %	70 - 95 %	0 - 10 %

Note : The above value may change as per raw materials procurement and figures do not show 100% accuracy.